
ASME B16.47 SERIES B · ASME B16.47-2025

# B16.47 B Class 900 26″ Blind

DN650 · Blind · Dimensions mm · Weight kg

**ASME B16.47 Series B · 26″ (DN650) · Class 900 · Blind Flange**




Both views share one scale (1:16); schematic only

Unit: mm

| Symbol | Item | Value |
|---|---|---|
| D | Outside diameter | 1022 mm |
| C | Flange thickness / blind thickness | 154 mm |
| D2 | Raised face diameter | 762 mm |
| f | Raised face height | 6.4 mm |
| K | Bolt circle diameter | 901.7 mm |
| n | Number of bolt holes | 20 pcs |
| d | Bolt hole diameter | 66.7 mm |
| — | Approximate weight | 991 kg |

## PRESSURE–TEMPERATURE RATINGS · CLASS 900 · GROUP 1.1

| | | | |
|---|---|---|---|
| ≤ 38 °C<br>153.1 bar | 50 °C<br>149.3 bar | 100 °C<br>140.1 bar | 150 °C<br>135.2 bar |
| 200 °C<br>131.5 bar | 250 °C<br>125.9 bar | 300 °C<br>119.7 bar | 325 °C<br>116.0 bar |
| 350 °C<br>112.9 bar | 375 °C<br>109.2 bar | 400 °C<br>103.9 bar | 425 °C<br>86.2 bar |
| 450 °C<br>68.9 bar | 475 °C<br>52.5 bar | 500 °C<br>34.6 bar | 538 °C<br>17.4 bar |

Source: Table 3 (p. 14) — pressure–temperature ratings for Group 1.1 materials, SI units; Group 1.1.

## MATERIAL AND NOTES

**Base material:** ASTM A105 (North America, Middle East)

**Rating:** Series B follows the former API 605 dimensions, with a smaller outside diameter and a different bolt pattern from Series A. Ratings are ASME classes 150, 300, 400, 600 and 900, with allowable pressure from the B16.47 tables.

**Tolerances / marking:** Tolerances, material and marking: ASME B16.47-2025. Series B and Series A are not interchangeable.

## NOTES / SPECIAL REQUIREMENTS

Work order _____ Inspector _____ Date _____ Travels with the part; file after inspection

**Source:** ASME B16.47-2025, Series B; dimensions transcribed from ASME B16.47-2025, verified 2026-11-04. Sheet #241.

This sheet is a factual compilation of published standards tables and is not a substitute for the standard itself. Verify dimensions and ratings against the edition named in your purchase specification before quoting, manufacturing or inspecting a critical part.

Scan to open